



The Pioneer Of Geosynthetics

S I N C E 1 9 7 2

HIGH PERFORMANCE GSE CONDUCTIVE TEXTURED GEOMEMBRANE (SINGLE-SIDED)

High Performance GSE Conductive Textured is a co-extruded high density polyethylene (HDPE) geomembrane specifically designed to be used in the most stringent applications. A textured surface is available on the top layer for applications that require increased frictional resistance. This product Smooth incorporates an electrically conductive bottom layer which can be spark tested for leak location in a safe, effective, and cost efficient method per ASTM D 7240. It contains only the finest raw materials to enable exceptional elasticity, environmental stress crack resistance, and excellent multi-axial break resistance. Included in this product is a custom additive package that has been engineered to enable extended geomembrane lifetime and improved resilience in elevated temperatures, hazardous waste containment, or a harsh chemical environment. In addition to a superior UV stabilization package, a well-dispersed premium grade of carbon black is utilized in the non-conductive layers to deliver superb UV resistance in exposed applications.

Product Specifications

These product specifications exceed GRI GM 13.

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM AVERAGE VALUE			
			40 mil	60 mil	80 mil	100 mil
Thickness, (minimum average) mil (mm) Lowest individual reading (-10%)	ASTM D 5994	every roll	40 (1.00) 36 (0.91)	60 (1.50) 54 (1.40)	80 (2.00) 72 (1.80)	100 (2.50) 90 (2.30)
Density, g/cm ³	ASTM D 1505	200,000 lb	0.94	0.94	0.94	0.94
Tensile Properties (each direction) Strength at Break, lb/in-width (N/mm) Strength at Yield, lb/in-width (N/mm) Elongation at Break, % Elongation at Yield, %	ASTM D 6693, Type IV Dumbbell, 2 ipm G.L. 2.0 in (51 mm) G.L. 1.3 in (33 mm)	20,000 lb	75 (13) 90 (15) 200 13	115 (20) 132 (23) 200 13	155 (27) 177 (31) 200 13	230 (40) 225 (39) 200 13
Tear Resistance, lb (N)	ASTM D 1004	45,000 lb	32 (142)	45 (200)	60 (266)	75 (333)
Puncture Resistance, lb (N)	ASTM D 4833	45,000 lb	95 (422)	130 (578)	160 (711)	190 (845)
Multi-axial Break Resistance, %	ASTM D 5617	per formulation	15	15	15	15
Carbon Black Content ⁽¹⁾ , % (Range)	ASTM D 1603*/4218	20,000 lb	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	45,000 lb	Note ⁽²⁾	Note ⁽²⁾	Note ⁽²⁾	Note ⁽²⁾
Asperity Height ⁽³⁾ , mil (mm)	ASTM D 7466	second roll	18 (0.45)	18 (0.45)	18 (0.45)	18 (0.45)
Notched Constant Tensile Load ⁽⁴⁾ , hr	ASTM D 5397, Appendix	200,000 lb	1,000	1,000	1,000	1,000
Oxidative Induction Time, mins	ASTM D 3895, 200°C; O ₂ , 1 atm	200,000 lb	>160	>160	>160	>160
High Pressure Oxidative Induction Time, mins	ASTM D 5885, 150°C; O ₂ , 3.4 MPa	per formulation	>800	>800	>800	>800
Oven aging at 85°C High Pressure OIT (min. avg.) - % retained after 90 days	ASTM D 5721 ASTM D 5885	per formulation	80	80	80	80
UV Resistance High Pressure OIT (min. avg.) - % retained after 1,600 hours	GM 11 ASTM D 5885	per formulation	80	80	80	80
TYPICAL ROLL DIMENSIONS						
Roll Length ⁽⁵⁾ , ft (m)	Single-Sided Textured		650 (198)	420 (128)	320 (98)	250 (76)
Roll Width ⁽⁵⁾ , ft (m)			22.5 (6.86)	22.5 (6.86)	22.5 (6.86)	22.5 (6.86)
Roll Area, ft ² (m ²)	Single-Sided Textured		14,625 (1,359)	9,450 (878)	7,200 (669)	5,625 (523)

NOTES:

- ⁽¹⁾High Performance GSE Conductive may have an overall ash content greater than 3.0% due to the conductive layer. These values apply to the non-conductive black layer only.
- ⁽²⁾Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.
- ⁽³⁾Consult GSE for information regarding asperity heights exceeding the specified values.
- ⁽⁴⁾NCTL for High Performance GSE Conductive Textured is conducted on representative smooth geomembrane samples.
- ⁽⁵⁾Roll lengths and widths have a tolerance of ± 1%.
- High Performance GSE Conductive Textured is available in rolls weighing approximately 3,900 lb (1,769 kg).
- All GSE geomembranes have dimensional stability of ±2% when tested according to ASTM D 1204 and LTB of <-77° C when tested according to ASTM D 746.
- *Modified.

NORTH AMERICA 800.435.2008 281.443.8564 • EUROPE & AFRICA 49.40.767420 • ASIA PACIFIC 66.2.937.0091 • SOUTH AMERICA 56.2.595.4200 • MIDDLE EAST 20.23.828.8888

gseworld.com

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Specifications subject to change without notice.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, LLC in the United States and certain foreign countries. REV FEB2012