



Material and Performance Specification

ECSC-3 Straw/Coconut Turf Reinforcement Mat

Description: The ECSC-3 is made with uniformly distributed 70% agricultural straw, 30% coconut fiber and three polypropylene nets securely sewn together with UV stabilized thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECSC-3 is a permanent turf reinforcement mat and is suitable for 1:1 slopes and high-flow channels.

Materials:

	Netting – Top and Bottom		Matrix		Thread
	Mediumweight UV Stabilized Polypropylene 0.50" x 0.50" Opening		70% Agricultural Straw 0.385 lbs yd ² 208.9 g/m ²		UV Stabilized 1.50" stitch spacing
	<i>Middle Netting</i> Heavyweight 24# PMSF UV Stabilized Polypropylene 0.40" x 0.50" Opening		30% Coconut Fiber 0.165 lbs yd ² 89.5 g/m ²		

Roll Size:

	Standard	Mega
Width:	7.5 ft (2.3 m)	15.0 ft (4.6 m)
Length:	120.0 ft (36.6 m)	120.0 ft (36.6 m)
Weight ±10%:	92.0 lbs (41.7 kg)	184.0 lbs (83.4 kg)
Area:	100 yd ² (83.6 m ²)	200 yd ² (167.2 m ²)
#/Pallet:	9	9

Index Value Properties*:

Property	Test Method	Typical
Mass/Unit Area	ASTM D6475	15.0 oz/yd ² (508.6g/m ²)
Thickness	ASTM D6525	.39 in (9.9 mm)
Tensile Strength-MD	ASTM D6818	756 lb/ft (11.0 kN/m)
Elongation-MD	ASTM D6818	20.7 %
Tensile Strength-TD	ASTM D6818	632 lb/ft (9.2 kN/m)
Elongation-TD	ASTM D6818	20.8 %
Light Penetration	ASTM D6567	7 %
UV Resistance	ASTM D4355-500hr	80 %
Density/Specific Gravity	ASTM D792	0.919 g/cm ³
* May differ depending upon raw material variations		

Bench-Scale Testing* (NTPEP*):**

Test Method	Parameters	Results
ECTC Method 2 Rainfall	50mm (2in) / hr-30 min	SLR**=18.16
	100mm (4in) / hr-30 min	SLR**=17.83
	150mm (6in) / hr-30 min	SLR**=17.50
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.63 lb/ft ²
ECTC Method 4 Germination	Top soil; Fescue; 21 day incubation	497% improvement
*Bench scale tests should not be used for design purposes.		
**Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor		
***The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO		

Slope Performance Design Values*:

Property	Test Method	Value	
Manning's N		0.024	
C-Factors	ASTM D6459		
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1
< 50 ft (15 m)	0.006	0.012	0.072
50 ft – 100 ft	0.026	0.042	0.086
>100 ft (30 m)	0.062	0.082	0.132
*Large-Scale Results obtained by 3 rd Party GAI Accredited Independent Laboratory			

Channel Performance Design Values*:

Property	Test Method	Value
Unvegetated Shear Stress	ASTM D 6460	2.79 lbs/ft ² (134 Pa)
Unvegetated Velocity	ASTM D 6460	11.0 ft/s (3.4 m/s)
Vegetated Shear Stress	ASTM D 6460	10.0 lbs/ft ² (478 Pa)
Vegetated Velocity	ASTM D 6460	20.0 ft/s (6.1 m/s)
*Large-Scale Results obtained by 3 rd Party GAI Accredited Independent Laboratory		



The values presented are for guidance purposes and do not constitute the practice of engineering. East Coast Erosion Blankets LLC (ECEB) ascertains that at the time of manufacture, all information presented herein is accurate and reliable and falls within the ECEB manufacturing product specification variances. If the product does not meet the stated values and ECEB is notified in writing prior to installation, the product will be replaced at no cost to the purchaser. ECEB will not be held liable for any type of damage or losses, directly, or indirectly for failure of this product. Current revision supersedes all previous versions for this product.