



Fortrac® 45

Data Sheet

Earthworks and Foundations

HUESKER's Fortrac® 45T geogrid is comprised of high tenacity polyester yarns crafted into a stable interlocked pattern then coated for protection from installation damage and short term ultraviolet exposure. Fortrac® geogrids are easy to install, unaffected by freeze-thaw conditions and naturally occurring chemical/biological environments. Fortrac® is utilized as a tensile element in retaining wall, steepened slope and void bridging applications, to name a few. Fortrac® geogrids are produced at HUESKER's manufacturing facility which has achieved ISO 9001 approval for its systematic approach to quality in development, manufacture, inspection, sales and application support for geosynthetic materials. HUESKER's ISO 9001 certificate is available upon request.

Physical Properties of Fortrac® 45T

PROPERTY	TEST	ENGLISH units ¹	SI units ¹
Mass/Unit Area	ASTM D-5261	5.9 oz/yd ²	201 g/m ²
Aperture Size	Measured	1x1 inch	25 x 25 mm
Percent Open Area	CWO 22125	70%	70%
Ultimate Wide Width Tensile Strength			
Machine Direction (MD)	ASTM D-6637	3,080 lb/ft	45 kN/m
Elongation at Ultimate Tensile Strength (MD)	ASTM D-6637	≤10%	≤10%
Long Term Design Strength* (MD)			
Sand, Silt and Clay	GRIGG4(b)	1,654 lb/ft	24.1 kN/m

¹Minimum average roll values are based on a 95% confidence level. MD-Machine Direction CMD-Cross Machine

Standard Roll Size: 16.41 ft (5.0 m) wide x 328.1 ft (100 m) long = 598 yd² (500 m²)
 Weight(includes core) = 270 lbs. (122 kg)

Each roll of Fortrac® geogrid delivered to the project site is labeled by HUESKER with a roll label that indicates manufacturer's name, product identification, lot number, roll number and roll dimensions. All rolls of Fortrac® are encased in a sturdy polyethylene wrap to shield the product from rain, dirt, dust and UV exposure. Contact HUESKER for information on our material warranty.

