

PRODUCT SPECIFICATION

CoolGuard® HRL36

1.0 BASE FABRIC

1.1	Base Fabric Weight	8	oz/yd ²	(270	g/m ²)
1.2	Fiber / Style	Polyester / Leno			

2.0 COATED FABRIC

2.1	Thickness (±10%)	36	mils	(0.91	mm)
2.2	Total Weight (nominal)	30	oz/yd ²	(1,015	g/m ²)
2.3	Coating Type	Ethylene Terpolymer PVC Alloy			
2.4	Coating Distribution	50 / 50			
2.5	Sealing Properties	<input checked="" type="checkbox"/>	Dielectric	<input checked="" type="checkbox"/>	Thermal

3.0 MATERIAL PROPERTIES (Minimum)

Standard

Metric

ASTM TEST METHODS

3.1	Tensile Strength, Grab					
	Warp (MD)	625	lbs	2,780	N	D751A
	Fill (TD)	600	lbs	2,670	N	
3.2	Tear Strength, Tongue					
	Warp (MD)	120	lbs	534	N	D751B (Mod)
	Fill (TD)	120	lbs	534	N	
3.3	Puncture, Flat Tip	220	lbs	979	N	D4833
3.4	Puncture, Ball	1,000	lbs	4,450	N	D751
3.5	Puncture, Pyramid	375	lbs	1,670	N	FTMS 101C, 2031
3.6	Hydrostatic Resistance	800	psi	5.52	MPa	D751A
3.7	Dimensional Stability (212°F/1 hr)	2.5	% max	2.5	% max	D1204
3.8	Ply Adhesion	25	lbs/2 in	111	N/5 cm	D751 (Mod)
3.9	Thermal/R.F. Adhesion	20	lbs/in	35	N/cm	D751
3.10	Low Temp Bend (1" mandrel)	-40	°F max	-40	°C max	D2136
3.11	UV Resistance	8,000	hrs	8,000	hrs	G23

A variety of standard widths and colors are available. Contact Cooley Engineered Membranes for details.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.