The COOLEY Group

PRODUCT SPECIFICATION L1023DEP

1.0 BASE FABRIC

1.1	Base Fabric Weight	5.08	oz/yď²	173	g/m²							
1.2	Fiber / Style		Polye									
2.0 COATED FABRIC												
2.1	Total Weight	23 <u>+</u> 2	oz/yď²	782 <u>+</u> 68	g/m ²							
2.2	Thickness	30 <u>+</u> 5	mils	0.76 <u>+</u> 0.13	mm							
2.3	Coating Type	Urethane										
2.4	Coating Distribution	60/40										
2.5	Sealing Properties		Dielectric		\square	Thermal						
							ASTM '	TEST				

3.0 MATERIAL PROPERTIES		Standard		Met	<u>ric</u>	METHODS	
3.1	Tensile Strength, Grab						
	Warp Fill	350 300	lbs Ibs	1,560 1,330	N N	D751-A	
3.2	Tensile Strength, 1" Strip						
	Warp Fill	240 200	lbs Ibs	1,070 890	N N	D751-B	
3.3	Tear Strength, Tongue						
	Warp Fill	160 160	lbs Ibs	712 712		D751-B (mod)	
3.4	Puncture, Screwdriver	75	lbs	334	Ν	D751	
3.5	Puncture, Ball	500	lbs	2,220	Ν	D751	
3.6	Hydrostatic Resistance	400	psi	2.8	MPa	D751-A	
3.7	Ply Adhesion	35	lbs/2 in	155	N/5 cm	D751 (mod)	
3.8	Adhesion Thermal	45	lbs/in	79	N/cm	D751	
3.9	Low Temp	-65	°F	-54	°C	D2136	
3.10	High Temp, Cont/Interm.	160 / 180	°F	71 / 82	°C	D1204	
	Abrasion Resistance (Wheel H18 / 1 kg)	5,000	cycles	5,000	cycles	D3884	

COMMENTS: Hydraulic conductivity = 1 x 10⁻⁶ cm/sec (max)

A variety of standard widths and colors are available. Contact Cooley Engineered Membranes for details.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.