Cooley/Engineered Membranes

WHERE CHEMISTRY MAKES THE DIFFERENCE

Rev Date: 5-27-09 Ref: 5-21-07

By: LSR

PRODUCT SPECIFICATION

1.0 STYLE

CoolPro® UPP (Unreinforced)

2.0 MATERIAL PROPERTIES 2.1 Thickness (±10%) 2.3 Resin Type		<u>UPP60</u> 60 <i>mil</i> ◀		<u>UPP80</u> 80 <i>mil</i> Polypropylene -		UPP100 100 mil		
3.0 MEC	CHANICAL PROPERTIES							ASTM TEST METHODS
3.1	Tensile Strength	108	lbs/in	144	lbs/in	180	lbs/in	D6693
3.2	Tensile Elongation	700	%	700	%	700	%	D6693
3.3	Tear Resistance	24	lbs	30	lbs	43	lbs	D1004
3.4	Puncture Resistance	45	lbs	54	lbs	68	lbs	D4833
3.5	Dimensional Stability	<u>+</u> 1	% max	<u>+</u> 0.5	% max	<u>+</u> 0.5	% max	D1204
3.6	Low Temperature	-40	°F	-40	°F	-40	°F	D2136
3.7	Stress Crack Resistance	3,000	hrs	3,000	hrs	3,000	hrs	D1693
3.8	UV Resistance (black)	35,000	hrs	35,000	hrs	35,000	hrs	G154
3.9	Ozone Resistance (100 pphm / 104°F / 7 days)	Pass		Pass		Pass		D1149

A variety of standard widths and colors are available including **NSF 61 certified** material. Contact Cooley Engineered Membranes for details.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.