

PRODUCT SPECIFICATION

1.0 STYLE

CoolPro<sup>®</sup> RPP36

2.0 COATED FABRIC

	<u>Standard</u>	<u>Metric</u>
2.1 Thickness ( $\pm 10\%$ )	36 mil	0.91 mm
2.3 Type of Coating	Polypropylene	
2.4 Coating Distribution	50 / 50	

3.0 MECHANICAL PROPERTIES

		<u>Standard</u>	<u>Metric</u>	ASTM TEST METHODS
3.1 Breaking Strength	Warp (MD)	275 lbs	1220 N	D751A
	Fill (TD)	250 lbs	1110 N	
3.2 Tear Strength	Warp (MD)	70 lbs	311 N	D751B (mod)
	Fill (TD)	70 lbs	311 N	
3.3 Wide Width Strength	Warp (MD)	150 lbs/in	262 N/cm	D4885
	Fill (TD)	125 lbs/in	219 N/cm	
3.3 Hydrostatic Resistance		350 psi	2.4 MPa	D751A
3.4 Puncture Resistance		300 lbs	1330 N	FTMS 101C, 2031
3.5 Ply Adhesion		40 lbs/2 in*	178 N/5 cm*	D751 (mod)
3.6 Dimensional Stability		1 % max	1 % max	D1204
3.7 Low Temperature		-40 °F	-40 °C	D2136
3.8 Abrasion Resistance (H18 / 1 kg)		5,000 cycles	5,000 cycles	D3884
3.9 Stress Crack Resistance		3,000 hrs	3,000 hrs	D1693
3.10 UV Resistance (black)		35,000 hrs	35,000 hrs	G154
3.11 Ozone Resistance (100 pphm / 14 days)		No Cracks	No Cracks	D1149

4.0 FACTORY SEAM PROPERTIES

4.1 Bonded Seam Strength	200 lbs	890 N	D751, NSF Mod.
4.2 Peel Adhesion	20 lbs/in*	35 N/cm*	D413

COMMENTS

- Ply Adhesion and Peel Adhesion testing may result in a film tearing bond (FTB) if the strength between layers is greater than the strength of the material itself.

A variety of standard widths and colors are available including NSF 61 certified material. Contact Cooley Engineered Membranes.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.