



Revised 16-Aug-2012

## TITAN TE-UX35PET

### UNI-AXIAL PET GEOGRID

Titan™ **TE-UX series** coated Polyester (PET) geogrids are specifically designed for improved performance in soil reinforcement applications where strength develops uni-axially. **TE-UX series** geogrids are manufactured with high molecular weight, high tenacity polyester yarns by precision knitting process. The Titan polyester geogrids is dimensionally stable with uniform network of apertures providing significant tensile reinforcement capacity in two principal directions. The Titan UX Polyester geogrid is engineered to be mechanically and chemically stable, in both harsh construction installation phase and in aggressive soil environments (pH level 3.0 – 12.0). Titan UX Polyester geogrids are biologically unaffected by soil micro –organisms. A black PVC saturation coating provides further chemical, mechanical, as well as ultraviolet protection.

| INDEX PROPERTIES   |    | TEST METHOD | UNIT MEASURE  | TE-UX35PET                    |
|--|----|-------------|---------------|-------------------------------|
| Ultimate Tensile Strength <sup>(1)</sup>                                       | MD | ASTM D 6637 | KN/m (lbs/ft) | 70.0 (4,798)                  |
| Tensile Strength at 5% strain <sup>(1)</sup>                                   | MD | ASTM D 6637 | KN/m (lbs/ft) | 28.7 (1,967)                  |
| Strain at Ultimate <sup>(2)</sup>  | MD | ASTM D 6637 | %             | <13                           |
| LONG TERM DESIGN PROPERTIES  |    |             |               |                               |
| Creep Reduced Strength <sup>(1)</sup>  | MD | ASTM D 5262 | KN/m (lbs/ft) | 44.30 (3,036)                 |
| Long Term Design Strength <sup>(1)</sup> <sup>(3)</sup> (sand, silt and clay ) | MD | GR1-GG4b    | KN/m (lbs/ft) | 38.35 (2,629)                 |
| Molecular weight (Min)   |    | GR1-GG8     | g/mol         | 31,000                        |
| Carboxyl End Group- CEG Count (Max )   |    | GR1-GG7     | mMol/Kg       | 25                            |
| PHYSICAL PROPERTIES  |    |             |               |                               |
| Roll Width <sup>(4)</sup>  |    | Minimum     | ft (m)        | 8.20 ( 2.5 )<br>16.40 ( 5.0 ) |
| Roll Length <sup>(4)</sup>   |    | Minimum     | ft (m)        | 164.04 (50.0)                 |

**Notes :** (1) Minimum Average Roll Values (MARV) Values- calculated as( Mean minus 2X standard deviation) (2) Average, (3) LTDS or Tal= Tult/ ( RFcreep X RF installation damage X RF durability ) for sand, silt and clay ), soil Dmax ≤ 25mm, D50 < 0.2mm . Reduction factor due to installation damage for other soil types is available on request. (4) Typical- Standard roll lengths are shown; the products may be fabricated to custom lengths to suit the contractor's requirements

#### Titan TE UX35PET Typical Applications:

- Steep Slope reinforcement
- Retaining wall reinforcement
- Bridge abutments
- Gabion retaining walls
- Vegetated retaining walls
- Landfill expansion projects
- Railway embankments
- Veneer Reinforcement
- Earth Bunds around oil Tanks

This data is provided for informational purposes only. Titan Environmental Containment Ltd. makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Titan Environmental Containment Ltd. for current updates.

**Titan Environmental Containment Ltd.**

777 Quest Blvd • Ile des Chenes, Manitoba • R0A0T0 • CANADA

Phone: +1.204.878.3955 Fax: +1.204.878.3980 Toll Free: +1.866.327.1957